



# 1792 HOTMARKPRINT



1792 & 1795 Class 1

PU	2 mil	45° Blade	MEDIUM pressure	320°F	20s	PEEL: WARM
----	-------	--------------	--------------------	-------	-----	------------

**CARRIER: Self-Adhesive And Clear Polyester**

### APPLIES ON

Cotton  
Polyester  
Acrylic & Similar  
Fabrics

### CARE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

### WASH

- Max 140°F
- Preferably inside out
- Do NOT bleach
- Tumble-dry
- Do NOT Dry-clean

### STORE

- Up to 1 year
- In a dry room (60-75°F)
- Away from sunlight
- In vertical position, in a plastic bag protected from dust

## APPLICATION

1. Prepare your design right-reading (DO NOT MIRROR) following the instruction of the printer manufacturer. NOTE: It is recommended to use OEM printer inks. Printable medias are very sensitive: always handle with care, preferably with gloves.
2. Set your printing temperature to 45°C and drying temperature to 50°C.
3. Use the adequate printing profile (for instance, with Roland COLORIP or VersaWorks, select the profile GENERIC VINYL 1, and we recommend to select the option MAX IMPACT).
4. Remove the product from the printer and wait for the complete drying of inks at room temperature, at least 4 hours.
5. Weed the excess material.
6. Use an application tape ATT 450 (with a medium tack) to transfer your design.
7. Position and heat press your design on the garment protected by a silicone paper at 320°F–20 seconds – medium pressure.
8. If you used tape, peel it off when warm.



**ieion**<sup>TM</sup>  
CORPORATION



Equipment



Supplies



Spare Parts



Software



Tools



Support

